



MLQ®Xtra

~AISI P20mod - 1.2738mod (HH) Remelted
PREMIUM QUALITY
PREHARDENED MOLD STEEL

TYPICAL APPLICATIONS

- Clear lens molds
- Mirror surface finish molds (SPI A-1 and sharper)
- Long run molds
- Abrasive plastic injection molds
- Reinforced plastic injection molds
- Dies for non corrosive plastic extrusion

GENERAL

Delivery Condition: Hardened and tempered
 Electroslag Remelted (ESR) or
 Vacuum Arc Remelted (VAR)
 Surface Hardness Range:

| | BHN | HRC | N/mm ² |
|-------------|---------|-------|-------------------|
| MLQ®Xtra 40 | 363-401 | 39-43 | 1255-1393 |

Other hardnesses available on demand

MLQ®Xtra is a new patented prehardened mold steel grade specially designed for through hardenability, ease of machining and simple post-production mold maintenance. It has high impact strength and excellent temper resistance. The well-balanced chemistry assures homogeneous hardness and near no section hardness loss due to mass.

MLQ®Xtra is forged on our largest presses equipped with wide dies assuring maximum deformation during forging process.

MLQ®Xtra is forged using a special densifying process which assures optimum consolidation of centers.

Typical Chemical Analysis - % weight

| C | Mn | Si | Ni | Cr | Mo | Other |
|------|------|------|------|------|------|----------------|
| 0.26 | 1.00 | 0.35 | 0.60 | 1.45 | 0.55 | Micro alloying |

MLQ®Xtra is an excellent material for Polishing, Photo-Etching & Texturing. The Remelting Process, Vacuum Degassing followed by Vacuum Arc Remelting or Electroslag Remelting process eliminates nearly all segregation and inclusions.

MLQ®Xtra is quenched in water. Best properties in steel are produced with the highest achievable quench severity.

MLQ®Xtra is characterized by :

- Highest thermal conductivity
- Improved through hardenability
- Best polishability
- Excellent weldability
- Uniform hardness
- Improved wear resistance

MLQ®Xtra is 100 % ultrasonic tested to very stringent acceptance levels. It is defect free.

MLQ®Xtra high hardenability ensures hardness levels to be maintained at the working surfaces, even on large molds with deep impressions.

®Finkl Steel Trademark

DATA SHEET

PREMIUM QUALITY MOLD STEEL

MLQ®Xtra

MATERIAL CHARACTERISTICS

The benefits of through high hardness are :

- Stable and continued machining can be performed with (C.N.C.) automatic machines.
- A defect free machined surface can be obtained.
- Dimensional stability of parting lines.

Structure

After hardening and tempering, the structure of MLQ®Xtra consists of tempered martensite to fine bainite.

The benefits of the through hardness combined with a uniform and stable micro-structure are :

- For mold design, consistent properties are assured.
- The machining distortion is minimized in the finished mold.
- A uniform luster can be obtained upon surface polishing.

PROPERTIES MLQ®Xtra

• Cleanliness :



| Method | A | B | C | D |
|-----------|---------|-------|---|-------|
| ASTM E45 | ≤ 0.5 | ≤ 0.5 | 0 | ≤ 0.5 |
| DIN 50602 | K1 ≤ 10 | | | |

• Physical Properties :

| Thermal conductivity | Thermal expansion coefficient (10 ⁻⁶ K ⁻¹) | | | Thermal capacity | Density |
|----------------------|---|-----------|----------|------------------|---------|
| W/m*K (BTU/hr*ft*°F) | 25-100 °C | 25-300 °C | 25-400°C | (J/Kg*K) | - |
| >45 (26) | 12.3 | 13.7 | 14.8 | 620 | 7.68 |

• Mechanical Properties : Typical values for a 4" (101.6 mm) thick plate.

| Hardness range | Hardness BHN (HRC) | Y.S. 0.2 MPa (KSI) | UTS MPa (KSI) | EI (%) | Impact@RT J (Ft-lb) | |
|----------------|--------------------|--------------------|---------------|--------|---------------------|---------|
| | | | | | Long. | Trans. |
| 363-401 BHN | 363 (39) | 1082 (157) | 1179 (174) | > 15 | 60 (44) | 56 (41) |



DATA SHEET


PREMIUM QUALITY MOLD STEEL

MLQ[®]Xtra

HEAT TREATMENT

Attainable Hardness of MLQ[®]Xtra

Quenched from 1650 °F (900 °C) and Tempered 4 hours
(Size of section – 4" X 4" (101.6 mm X 101.6 mm))



Stress Relieving

Heat at a rate of one hour per inch (25.4 mm) of maximum thickness to 850 to 900 °F (454-482 °C) Hold at temperature for one hour per inch (25.4 mm) and air cool.

Tempering

Tempering treatments vary for different sizes and applications. The following instructions will provide through tempering:

Heat uniformly at the selected tempering temperatures and hold at temperature for one hour per inch (25.4 mm) of total thickness.

INDUCTION AND LASER HARDENING

MLQ[®]Xtra lends itself to induction or laser hardening of selective surfaces creating a surface hardness of up to 60-63 HRC varying in depth from skin hardness up to 0.125" (3 mm).

EDM (ELECTRIC DISCHARGE MACHINING)

This method of machining is widely used on prehardened MLQ[®]Xtra. However, precaution should be taken since this method of machining leaves a rehardened surface layer (white layer) on the steel. It is advisable to remove this layer.

HARD-CHROMIUM PLATING

After hard-chromium plating, the tool should be tempered for a minimum of four (4) hours at 350 °F (180 °C) in order to avoid hydrogen embrittlement. In case of replating, the tool should be tempered after it has been acid stripped.

TEXTURING

MLQ[®]Xtra offers excellent response to texturing because of the great homogeneity of its structure and patented low alloy composition.

DATA SHEET

PREMIUM QUALITY MOLD STEEL

MLQ®Xtra

POLISHING

Successful polishing requires talent, patience and experience. But some known basics are:

- Practice extreme cleanliness between steps to avoid carryover of contaminant particles
- Use high quality consumables
- Over polishing is detrimental to the steel surface leading to so called orange-peeling and pitting
- The following is an example of good hardpolishing procedure :

Preparation for diamond polishing

- Step 1 • Polish with 220 – grit silicon stone
- Step 2 • Polish with 320 – grit silicon stone
- Step 3 • Polish with 520 – grit silicon stone
- Step 4 • Polish with 800 – grit silicon stone
- Step 5 • Polish with diamond paste grade 15
- Step 6 • Polish with diamond paste grade 6
- Step 7 • Polish with diamond paste grade 3

When the demands for finish are particularly high, use grade 1. Be aware that the best result is obtained after a certain optimum polishing time.

Note: Provided technical data and information in this data sheet are typical values. Normal variations in chemistry, size and conditions of heat treatment may cause deviations from these values. We suggest that information be verified at time of enquiry or order. For additional data or metallurgical assistance, please contact us.

SIZE MLQ®Xtra (Finished / approx.)

| | | |
|---------------|---------------------|------------|
| Max weight | 16330 kg | 36000 lbs |
| Max section | 0.90 m ² | 1400 sq in |
| Max width | 1350 mm | 53" |
| Max thickness | 760 mm | 30" |

METALLURGICAL SERVICES

The Metallurgical Laboratory provides standard mechanical properties testing for *Tensile Testing* (ASTM A 370), *Impact Testing* (ASTM E 23), *Hardness Testing* (ASTM E 10, E 18, A 956), *Macroetch Testing* (ASTM E 381), and other metallurgical testing with certification of results where requested.

Metallurgical facilities are made available to customers through your sales representative to assist in analysis of technical issues that may arise during processing or performance of Finkl forgings. Reports and consultation are offered as a service to customers with the aim of improving product performance.

Finkl Steel—Chicago

1355 E. 93rd Street
Chicago, IL 60619

773.975.2510
TOLL-FREE: 800.621.1460
FAX: 773.348.5347
www.finkl.com

Finkl Steel—Sorel

100 McCarthy Street
St-Joseph-de-Sorel
Quebec, Canada J3R 3M8

450.746.4122
TOLL-FREE: 800.363.9484
www.sorelforge.com

Finkl Steel—Composite

2300 W. Jefferson Avenue
Detroit, MI 48216

313.496.8599
www.compforge.com



FINKL STEEL